

DECLARATION OF PERFORMANCE

N. CPR-ES2/0024

1 Unique identification code of the product-type	TECNOFOAM G-2040HFO Free of fluorinated gases (European Regulation 517/2014) PU EN 14315-1-CCC4-CT3(20)-TFT10(20)-FRB30(20)-W0,10-MU102
2 Intended uses	ThIB - Thermal insulation of buildings - In-situ formed dispensed rigid polyurethane foam system (PU)
3 Manufacturer	TECNOPOL SISTEMAS, S.L.U. Finlàndia, 33 08520 Les Franqueses del Vallès – Barcelona-Spain www.tecnopolgroup.com – t. +34 935682111
4 Systems of AVCP	AVCP – System 3
5 Harmonized standards	EN 14315-1:2013
Notified bodies	The notified testing laboratory CEIS/CENTRO DE ENSAYOS, INNOVACION Y SERVICIOS N.1722 performed the test reports on the other declared characteristics. The notified testing laboratory LGAI TECHNOLOGICAL CENTER, S.A/Applus N.0370 performed the reaction for fire test report.
6 Performances declared	
Essential characteristics	Performances
Reaction to fire:	Euroclass E
Water permeability:	Short-term water absorption by partial immersion: ≤0,10 kg/m ²
Thermal resistance:	See the performance chart
Water vapor permeability:	μ=102
Compressive strength:	NPD (No Performance Determined)
Durability of reaction to fire against ageing/degradation:	Reaction to fire does not decrease with time
Durability of thermal resistance against aging/ degradation:	See the performance chart; determined by an aging process
Durability of compressive strength against ageing/degradation:	The compression strength does not decrease with time
Continuous glowing combustion:	NPD (No Performance Determined)
7 REACH information	the information referred to Article 31 or, as appropriate, to Article 33 of the REACH Regulation (EC) no. 1907/2006 and the following amendments are indicated in the safety data sheet that TECNOPOL makes available on the website along with this current Declaration of Performance

PERFORMANCE CHART

Total thickness	Declared aged thermal conductivity W/m-K	Thermal resistance level R=m² ·K/W
30mm	0,028	1,10
35mm	0,028	1,30
40mm	0,028	1,40
45mm	0,028	1,60
50mm	0,028	1,80
55mm	0,028	2,00
60mm	0,028	2,10
65mm	0,028	2,30
70mm	0,028	2,50
75mm	0,028	2,70
80mm	0,026	3,10
85mm	0,026	3,30
90mm	0,026	3,50
95mm	0,026	3,70
100mm	0,026	3,80
105mm	0,026	4,00
110mm	0,026	4,20
115mm	0,026	4,40
120mm	0,025	4,80
125mm	0,025	5,00
130mm	0,025	5,20
135mm	0,025	5,40
140mm	0,025	5,60
145mm	0,025	5,80
150mm	0,025	6,00
155mm	0,025	6,20
160mm	0,025	6,40
165mm	0,025	6,60
170mm	0,025	6,80
175mm	0,025	7,00
180mm	0,025	7,20

The performance of the product identified above is in conformity with the set of declared performances.

This declaration of performance is issued, in accordance with Regulation (EU) no. 305/2011, under the sole responsibility of the manufacturer identified above.



Signed for and on behalf of the manufacturer by **David Pont – Technical Service Manager**

**Les Franqueses del Vallès,
12/12/2022**



DoP in Pdf format is available on the [Tecnopol website](http://www.tecnopol.es).

<i>Revision 0 notes:</i>	<i>First issue</i>
<i>Revision 1</i>	<i>Update of some performances (water absorption, water permeability)</i>
<i>Revision 2</i>	<i>Update of tests according to the fire according to the EN-13501</i>

 1722, 0370	 TECNOPOL SISTEMAS, S.L.U., Finlàndia, 33 08520 Les Franqueses del Vallès – Barcelona-Spain – www.tecnopolgroup.com																		
<p style="text-align: center;"> 21 CPR-ES2/0024 EN 14315-1:2013 TECNOFOAM G-2040HFO ThIB - Thermal insulation of buildings - In-situ formed dispensed rigid polyurethane foam system (PU) </p>																			
<table border="0"> <tr> <td>Reaction to fire:</td> <td>Euroclass E</td> </tr> <tr> <td>Water permeability:</td> <td>Short-term water absorption by partial immersion: $\leq 0,10 \text{ kg/m}^2$</td> </tr> <tr> <td>Thermal resistance:</td> <td>See the performance chart</td> </tr> <tr> <td>Water vapor permeability:</td> <td>$\mu=102$</td> </tr> <tr> <td>Compressive strength:</td> <td>NPD (No Performance Determined)</td> </tr> <tr> <td>Durability of reaction to fire against ageing/degradation:</td> <td>Reaction to fire does not decrease with time</td> </tr> <tr> <td>Durability of thermal resistance against aging/ degradation:</td> <td>See the performance chart; determined by an aging process</td> </tr> <tr> <td>Durability of compressive strength against ageing/degradation:</td> <td>The compression strength does not decrease with time</td> </tr> <tr> <td>Continuous glowing combustion:</td> <td>NPD (No Performance Determined)</td> </tr> </table>		Reaction to fire:	Euroclass E	Water permeability:	Short-term water absorption by partial immersion: $\leq 0,10 \text{ kg/m}^2$	Thermal resistance:	See the performance chart	Water vapor permeability:	$\mu=102$	Compressive strength:	NPD (No Performance Determined)	Durability of reaction to fire against ageing/degradation:	Reaction to fire does not decrease with time	Durability of thermal resistance against aging/ degradation:	See the performance chart; determined by an aging process	Durability of compressive strength against ageing/degradation:	The compression strength does not decrease with time	Continuous glowing combustion:	NPD (No Performance Determined)
Reaction to fire:	Euroclass E																		
Water permeability:	Short-term water absorption by partial immersion: $\leq 0,10 \text{ kg/m}^2$																		
Thermal resistance:	See the performance chart																		
Water vapor permeability:	$\mu=102$																		
Compressive strength:	NPD (No Performance Determined)																		
Durability of reaction to fire against ageing/degradation:	Reaction to fire does not decrease with time																		
Durability of thermal resistance against aging/ degradation:	See the performance chart; determined by an aging process																		
Durability of compressive strength against ageing/degradation:	The compression strength does not decrease with time																		
Continuous glowing combustion:	NPD (No Performance Determined)																		

Note:

TECNOPOL SISTEMAS S.L.U, supplies the current annex along with the DoP to make the consultancy of the CE marking easier for the international clients. The enclosed CE marking can be slightly different compared to the one printed on the relevant packaging or documentation because of:

- graphic adaptations due to lack of space on the packaging or printing methods used,
- different language (the same packaging can be shared by several countries),
- the product is already in stock when the updating of the CE marking is implemented,
- printing mistakes